



# COMMERCIAL TESTING COMPANY

Post Office Box 985 • 1215 South Hamilton Street • Dalton, Georgia 30722  
Telephone (706) 278-3935 • Facsimile (706) 278-3936

Standard Method of Test for  
Surface Burning Characteristics of Building Materials

ASTM E 84-06

**Aqua Plus Pigment 639**

HR-105 PU

Report Number 06-12182

Test Number 3845-4121

December 8, 2006

Vitrulan Corporation  
Waynesboro, Virginia

Commercial Testing Company is accredited for the ASTM E 84 test by the United States Department of Commerce, National Institute of Standards and Technology (NIST), through the National Voluntary Laboratory Accreditation Program (NVLAP) for conformance with criteria set forth in NIST Handbook 150:2001, and all requirements of ISO/IEC 17025:1999.

Commercial Testing Company

(Authorized Signature)

*This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. The test results presented in this report apply only to the samples tested and are not necessarily indicative of apparent identical or similar materials. Sample selection and identification were provided by the client. A sampling plan, if described in the referenced test procedure, was not necessarily followed. This report, or the name of Commercial Testing Company, shall not be used under any circumstance in advertising to the general public.*

**TESTED TO BE SURE®**  
Since 1974

## INTRODUCTION

This report is a presentation of results of a surface flammability test on a material submitted by Vitruvan Corporation, Waynesboro, Virginia.

The test was conducted in accordance with the ASTM International fire test response standard E 84-06, *Surface Burning Characteristics of Building Materials*, sometimes referred to as the Steiner tunnel test. This test is applicable to exposed surfaces such as walls and ceilings. The test is conducted with the specimen in the ceiling position with the surface to be evaluated exposed face down to the ignition source. The ASTM E 84 test method is technically identical to NFPA No. 255 and UL No. 723.

This standard is used to measure and describe the response of materials, products, or assemblies to heat and flame under controlled conditions, but does not by itself incorporate all factors required for fire-hazard or fire-risk assessment of materials, products, or assemblies under actual fire conditions.

## PURPOSE

The purpose of the test is to provide only the comparative measurements of surface flame spread and smoke development of materials with that of select grade red oak and fiber-reinforced cement board, Grade II, under specific fire exposure conditions. The test exposes a nominal 24-foot long by 20-inch wide test specimen to a controlled air flow and flaming fire adjusted to spread the flame along the entire length of a red oak specimen in 5.50 minutes. During the 10-minute test duration, flamespread over the specimen surface and density of the resulting smoke are measured and recorded. Test results are calculated relative to red oak, which has an arbitrary rating of 100, and fiber-reinforced cement board, Grade II, which has a rating of 0.

The test results are expressed as Flame Spread Index and Smoke Developed Index. The Flame Spread Index is defined in ASTM E 176 as "a number or classification indicating a comparative measure derived from observations made during the progress of the boundary of a zone of flame under defined test conditions." The Smoke Developed Index, a term specific to ASTM E 84, is defined as "a number or classification indicating a comparative measure derived from smoke obscuration data collected during the test for surface burning characteristics." There is not necessarily a relationship between the two measurements.

The method does not provide for measurement of heat transmission through the surface tested, the effect of aggravated flame spread behavior of an assembly resulting from the proximity of combustible walls and ceilings, or classifying a material as noncombustible solely by means of a Flame Spread Index.

The zero reference and other parameters critical to furnace operation are verified on the day of the test by conducting a 10-minute test using 1/4-inch fiber-reinforced cement board, Grade II. Periodic tests using NOFMA certified 23/32-inch select grade red oak flooring provide data for the 100 reference.

## TEST SAMPLE

The test sample, selected by the client, was identified as **Aqua Plus Pigment 639**, a wallcovering with a total weight of 4.8 ounces per square yard. Three test panels, each measuring two feet wide by eight feet in length, were prepared by adhering the material to 5/8-inch thick Type X gypsum wallboard using Roman Pro 838 Heavy Duty Clear Wallpaper Adhesive. The adhesive was applied with a 3/8" napped roller to the back of the wallcovering, booked 5 to 7 minutes, the material placed onto the face of the gypsum board and smoothed with a brush and roller. After drying overnight, one coat of an interior latex flat paint was rolled onto the wallcovering using a 3/8" napped roller at the manufacturers recommended coverage rate of 400 square feet per gallon. After a second overnight drying period, one coat of JFB Hart Coatings HP-105 two-part polyurethane coating was rolled onto the wallcovering using a 3/8" napped roller at the manufacturers recommended coverage rate of 250 square

feet per gallon. The prepared panels were transferred to storage racks and conditioned to equilibrium in an atmosphere with the temperature maintained at  $71 \pm 2^\circ\text{F}$  and the relative humidity at  $50 \pm 5$  percent. For testing, the panels were placed end-to-end on the ledges of the tunnel furnace and tested with no auxiliary support mechanism. This method of sample preparation is described in Appendix X1 of the E 84 standard, Guide to Mounting Methods, Section X1.9.4.

### TEST RESULTS

The test results, calculated on the basis of observed flame propagation and the integrated area under the recorded smoke density curve, are presented below. The Flame Spread Index obtained in E 84 is rounded to the nearest number divisible by five. Smoke Developed Indices are rounded to the nearest number divisible by five unless the Index is greater than 200. In that case, the Smoke Developed Index is rounded to the nearest 50 points. The flame spread and smoke development data are presented graphically on Page 4 of this report.

| Test Specimen                           | Flame Spread Index | Smoke Developed Index |
|-----------------------------------------|--------------------|-----------------------|
| Fiber-Reinforced Cement Board, Grade II | 0                  | 0                     |
| Red Oak Flooring                        | 100                | 100                   |
| Aqua Plus Pigment 639                   | 35                 | 15                    |

### OBSERVATIONS

Specimen ignition over the burners occurred at 0.30 minute. Surface flame spread was observed to a maximum distance of 7.33 feet beyond the zero point at 0.63 minute. The maximum temperature recorded during the test was  $628^\circ\text{F}$ .

### CLASSIFICATION

The Flame Spread Index and Smoke Developed Index values obtained by ASTM E 84 tests are frequently used by code officials and regulatory agencies in the acceptance of interior finish materials for various applications. The most widely accepted classification system is described in the National Fire Protection Association publication NFPA 101 *Life Safety Code*, where:

|         |                             |                               |
|---------|-----------------------------|-------------------------------|
| Class A | 0 - 25 Flame Spread Index   | 0 - 450 Smoke Developed Index |
| Class B | 26 - 75 Flame Spread Index  | 0 - 450 Smoke Developed Index |
| Class C | 76 - 200 Flame Spread Index | 0 - 450 Smoke Developed Index |

Class A, B, and C correspond to Type I, II, and III respectively in other codes such as SBCCI, BOCA, and ICBO. They do not preclude a material being otherwise classified by the authority of jurisdiction.

### ASTM E 84 TEST DATA

Client: Vitruvan Corporation

Test Number: 3845-4121

Material Tested: Aqua Plus Pigment 639

Date: December 8, 2006

#### Test Results:

Time to Ignition = 00.30 minutes  
Maximum Flamespread Distance = 07.33 feet  
Time to Maximum Spread = 00.63 minutes

Flame Spread Index = 35  
Smoke Developed Index = 15

